



441 DeGroate Rd., New Lenox, IL 60451  
 815-462-0939 Fax: 815-485-1194  
[www.dpswax.com](http://www.dpswax.com)  
 email: [info@dpswax.com](mailto:info@dpswax.com)

DPS/MORRIS WAX  
 A Division of Saco Petroleum

9807 Kaw Drive, Edwardsville, KS 66111  
 913-948-6220 Fax: 913-948-6242  
[www.sacopetroleum.com](http://www.sacopetroleum.com)



500 N. National, Springfield, MO 65804  
 417-869-7333 Fax: 417-831-4671  
[www.morriswax.com](http://www.morriswax.com)  
 email: [ghudson@morriswax.com](mailto:ghudson@morriswax.com)

## 1230 Paraffin Wax

**1230** is a fully refined paraffin wax used for containers.

### PHYSICAL PROPERTIES

TEST METHODS	ASTM METHOD	SPECIFICATIONS		TYPICAL
		Minimum	Maximum	
Melt Point °F (°C)	D-87	126 (52.2)	131 (55.0)	129 (53.9)
Kinematic Viscosity, cSt @210°F (98.9°C)	D-445	3.0	4.0	3.3
Saybolt Viscosity, SUS @ 210°F (98.9°C)	D-2161	36.2	39.5	37.2
Oil Content, Wt%	D-721	----	0.5	----
Saybolt Color	D-6045	+28	----	+30
Odor	D-1833	----	1	0
Needle Penetration, dmm @ 77°F (25°C)	D-1321	10	18	14

### SHIPPED:

10 lb. slabs in 60 lb. cartons or 2000 lb. covered gaylords or pastilles in 50 lb. bags

### FDA STATUS:

This product meets the FDA requirements set forth in 21 CFR 178.3710 for use in non-food articles in contact with food and in 21 CFR 172.886 for use in food.