



441 DeGroate Rd., New Lenox, IL 60451  
815-462-0939 Fax: 815-485-1194  
[www.dpswax.com](http://www.dpswax.com)  
email: [info@dpswax.com](mailto:info@dpswax.com)

DPS/MORRIS WAX  
A Division of Saco Petroleum

9807 Kaw Drive, Edwardsville, KS 66111  
913-948-6220 Fax: 913-948-6242  
[www.sacopetroleum.com](http://www.sacopetroleum.com)



500 N. National, Springfield, MO 65804  
417-869-7333 Fax: 417-831-4671  
[www.morriswax.com](http://www.morriswax.com)  
email: [ghudson@morriswax.com](mailto:ghudson@morriswax.com)

## 1250 Paraffin Wax

**1250** is a fully refined paraffin wax which will be a replacement for 1218 as of October 2006.

### PHYSICAL PROPERTIES

TEST METHODS	ASTM METHOD	SPECIFICATIONS		TYPICAL
		Minimum	Maximum	
Congearing Point °F (°C)	D-938	139.5 (59.7)	145.5 (63.1)	142.5 (61.4)
Kinematic Viscosity, cSt @212°F (100°C)	D-445	4.4	5.6	4.7
Oil Content, Wt%	D-721	----	0.7	----
Saybolt Color	D-6045	+28	----	+30
Odor	D-1833	----	1	0
Needle Penetration, dmm @ 77°F (25°C)	D-1321	----	----	11
Needle Penetration, dmm @ 90°F (32.2°C)	D-1321	----	----	18

### SHIPPED:

10 lb. slabs in 60 lb. cartons

### FDA STATUS:

This product meets the FDA requirements set forth in 21 CFR 178.3710 for use in non-food articles in contact with food and in 21 CFR 172.886 for use in food.