



441 DeGroat Rd., New Lenox, IL 60451
 815-462-0939 Fax: 815-485-1194
www.dpswax.com
 email: info@dpswax.com

DPS/MORRIS WAX
 A Division of Saco Petroleum

9807 Kaw Drive, Edwardsville, KS 66111
 913-948-6220 Fax: 913-948-6242
www.sacopetroleum.com



500 N. National, Springfield, MO 65804
 417-869-7333 Fax: 417-831-4671
www.morriswax.com
 email: ghudson@morriswax.com

2243

2243 is a specialty formulation of petroleum derived paraffin waxes used to make containers.

PHYSICAL PROPERTIES

TEST METHODS	ASTM METHOD	SPECIFICATIONS		TYPICAL
		Minimum	Maximum	
Melt Point °F (°C)	D 87	125 (51.7)	129 (53.9)	127 (52.8_)
Kinematic Viscosity, cSt @ 210°F (98.9°C)	D445	3.0	4.0	3.3
Saybolt Viscosity, SUS @ 210°F (98.9°C)	D2161	36.2	39.5	37.2
Oil Content, Wt%	D721	----	2.5	1.5
Saybolt Color	D6045	+26	----	+30
Odor	D1833	----	1	0
Needle Penetration, dmm @ 77°F (25°C)	D1321	14	30	22

FDA STATUS:

This product meets the FDA requirements set forth in 21 CFR 178.3710 for use in non-food articles in contact with food and in 21 CFR 172.886 for use in food.