



441 DeGroate Rd., New Lenox, IL 60451
815-462-0939 Fax: 815-485-1194
www.dpswax.com
email: info@dpswax.com

DPS/MORRIS WAX
A Division of Saco Petroleum

9807 Kaw Drive, Edwardsville, KS 66111
913-948-6220 Fax: 913-948-6242
www.sacopetroleum.com



500 N. National, Springfield, MO 65804
417-869-7333 Fax: 417-831-4671
www.morriswax.com
email: ghudson@morriswax.com

2281 - Therapeutic Wax

Therapeutic Wax is a specially selected grade of white crude scale wax possessing good flexibility as well as high gloss on air cooling. The storage life of vegetables such as turnips is improved by prevention of loss of moisture, while appearance is enhanced for improved marketability. Because it maintains flexibility at refrigerated temperatures, chipping and cracking of the coating is minimized when compared to other waxes.

PHYSICAL PROPERTIES

TEST METHODS	ASTM METHOD	SPECIFICATIONS		TYPICAL
		Minimum	Maximum	
Melt Point °F (°C)	D87	120 (48.9)	127 (52.8)	123 (50.5)
Kinematic Viscosity, cSt @210°F (98.9°C)	D445	3.2	4.2	3.7
Saybolt Viscosity, SUS @ 210°F (98.9°C)	D2161	37.0	40.0	38.5
Oil Content, Wt%	D721	---	2.0	1.5
Saybolt Color	D156	+25	---	+30
Odor	D1833	----	2	1
Needle Penetration, dmm @ 77°F (25°C)	D1321	20	70	55